White Noise Characterization of N-MOSFETs for Physics-Based Cryogenic Device Modeling

This paper was downloaded from TechRxiv (<https://www.techrxiv.org>).

LICENSE

CC BY 4.0

SUBMISSION DATE / POSTED DATE

05-01-2021 / 07-01-2021

CITATION

Ohmori, Kenji; Amakawa, Shuhei (2021): White Noise Characterization of N-MOSFETs for Physics-Based Cryogenic Device Modeling. TechRxiv. Preprint. <https://doi.org/10.36227/techrxiv.13520612.v1>

DOI

[10.36227/techrxiv.13520612.v1](https://doi.org/10.36227/techrxiv.13520612.v1)

White Noise Characterization of N-MOSFETs for Physics-Based Cryogenic Device Modeling

K. Ohmori and S. Amakawa

Device Lab Inc., Tsukuba, Ibaraki, Japan; Email: ohmori@devicelab.co.jp

Abstract

We propose a methodology of variable-temperature broadband noise characterization for cryogenic MOSFETs. A DUT is mounted on a reusable PCB *vehicle* with a built-in low-noise amplifier, and loaded into a cryogenic chamber. Using the vehicle, we measured flicker (low frequency) and white noise, and have successfully revealed dominance of shot noise in the temperature range from 300 to 120 K for the first time.

(Keywords: cryogenic CMOS, white noise, 1/f noise)

Introduction

Quantum computing is one of the challenging technologies that require the power of CMOS circuits be made available at cryogenic temperatures for maintaining the coherent time of qubits, such as electronic spin. A peripheral circuit for the control and readout of a quantum processor may be needed to operate at a temperature as low as 1 to 4 K [1]. Therefore, MOSFET compact models valid down to cryogenic temperatures are necessary [2]. At cryogenic temperatures, peculiar phenomena such as bandgap widening, carrier freezeout, and self-biasing appear. Continuous characterization of MOSFETs at varying temperatures starting from room temperature (RT) down to cryogenic temperature is important for building physics-based predictive models. In particular, wideband noise modeling is essential for the development of low-noise circuits interfacing with a quantum processor.

MOSFETs are known to exhibit flicker noise at low frequencies (LF) and white noise at high frequencies (HF). Physical origins of flicker noise and white noise differ, and therefore, their power spectral densities are independent of each other. White noise can be further classified into thermal noise and shot noise. Unlike the relationship between flicker noise and white noise, thermal noise and shot noise are not completely independent of each other [3-4].

A proof-of-concept noise probe for on-wafer broadband characterization was demonstrated using a dc-biased approach at RT, achieving HF noise measurement up to 800 MHz [5]. At present, an improved version of the noise probe is commercially available as Entrope[®] Noise Probe [6], details of which will be presented elsewhere [7]. In this study, we have applied the noise probe technology to an *in-situ* system of variable-temperature broadband noise measurements down to 120 K.

Experimental Setup and Measurement

We developed a reusable PCB vehicle for cryogenic measurements, which includes a broadband low-noise amplifier (LNA). Each vehicle is characterized and calibrated using our proprietary technology so that we obtain pure noise from a DUT without noise from the LNA. A DUT is mounted on the vehicle right next to the LNA. We employed a semiconductor device analyzer (B1500A, Agilent Technologies) for biasing DUTs and a spectrum analyzer (N9030A, Agilent Technologies) for reading the output from the LNA.

We characterized two types of N-MOSFETs, denoted by A and B, for demonstration of several kinds of noise characterization. The gate lengths are 240 nm for A and 120 nm for B. DUTs with 4 contact pads were mounted on vehicles by flip-chip bonding for stable measurements at different temperatures.

Variable-Temperature Characterization

A. Instrumental Setup and Dc Properties

The PCB vehicle is inserted in a cryogenic He chamber as schematically shown in **Fig. 1**. The temperature (T) range examined is from 5 to 300 K. If one uses a cryogenic probe station, the length of probe tips shrinks as T decreases, which makes stable continuous variable- T measurement very difficult. Therefore, it is beneficial also in this regard to bond a DUT next to an LNA.

Figure 2(a) shows I_d - V_g curves at 5–300 K. At low temperatures, I_d decreases in the subthreshold region and increases in the strong inversion region corresponding to the change in the transconductance (g_m) shown in **Fig. 2(b)**. Dependences of V_{th} and subthreshold swing (SS) on T are plotted in **Fig. 3**. SS becomes steep as T decreases. The V_{th} values shift higher as T decreases. We used the gate-source voltage (V_g) as biasing points in variable-temperature noise measurements instead of the gate overdrive voltage.

B. Pure Thermal Noise at Zero Drain Voltage

What is unique in this study using the vehicle is a capability of wideband noise characterization. **Figure 4** shows S_{Id} under a zero-drain-bias ($V_d = 0$ V) condition for V_g from 0.8 to 1.6 V, demonstrating successful measurement of white noise at (a) $T = 300$ and (b) 121 K. The frequency range is from 50 kHz to 100 MHz. Note that the maximum

measurable frequency in commercially available LF noise systems is a few tens of MHz at most. As V_g increases, the differential resistance $R_{\text{dif}} (= \partial V_d / \partial I_d)$ decreases, resulting in higher white noise levels.

Noise measurements were conducted continuously from 120 to 300 K. In **Fig. 5**, T dependence of S_{Id} at 10 MHz are plotted as a function of thermal noise intensity $S_{\text{th}} (= 4k_B T / R_{\text{dif}})$, where k_B is the Boltzmann constant. We observed a good linear relationship with the slope value of unity. As V_g and T change, the range of the linear relationship extends from 4×10^{-25} to $7 \times 10^{-23} \text{ A}^2/\text{Hz}$, which corresponds to the R_{dif} values from 23 k Ω to 188 Ω .

C. Shot-Noise Evaluation in the Linear Region

When a nonzero V_d is applied, I_d starts to increase and shot noise appears. In order to characterize white noise that consist of thermal and shot noise, noise measurement was conducted in the linear region for DUT A, where V_d ranges from 0 to 0.08 V as shown in **Fig. 6**. The change from flicker noise to white noise is clearly observed. We focus on white noise characterization in this study. Although the slope of $S_{\text{Id}}(f)$ becomes very small at high frequencies, the slope for large V_d values is not quite zero. Therefore, we estimated f_c and S_w by using

$$S_{\text{Id}}(f) = K_f / f^\beta + S_w, \quad (1)$$

where K_f is S_{Id} at 1 Hz, $-\beta (\approx -1)$ is the slope of flicker noise power spectrum on a log-log plot, and $(K_f / S_w)^{1/\beta}$ corresponds to the corner frequency (f_c). Extracted β and S_{Id} values at 10 and 30 MHz were used. As shown in **Fig. 7**, f_c gradually increases as T decreases mainly because the intensity of thermal noise decreases. The f_c value is higher for larger V_d due to higher LF noise intensity.

Figure 8 shows the dependence of S_{Id} and estimated S_w on V_d for $T =$ (a) 300 and (b) 130 K. Open circles and diamonds show measured S_{Id} at 10 and 30 MHz, respectively. Difference between these values becomes larger as V_d increase resulting from the increase in residual flicker noise. Thermal noise intensity S_{th} for nonzero-drain-bias conditions is given by [8]

$$S_{\text{th}} = 4k_B T R_{\text{ch}}(V_d) / [R_{\text{dif}}(V_d)]^2, \quad (2)$$

where $R_{\text{ch}} = V_d / I_d$ is the chord resistance [9].

Expected thermal noise S_{th} , full-shot noise $2qI_d$, and the sum of them are superimposed by the dashed, solid, and dot-dashed lines, respectively. At $V_d = 0$ V, the S_w value corresponds to thermal noise S_{th} and, as V_d increases, it increases along $2qI_d$. Shot noise is often characterized by using the so-called Fano factor and the $2qI_d$ value is the maximum limit of shot noise [10]. Thermal noise dominates

under low drain bias ($V_d \lesssim 2k_B T / q$) and shot noise becomes dominant when $V_d \gtrsim 2k_B T / q$, which is indicated by the red arrows.

Figure 9 shows correlation between S_w and thermal noise S_{th} for $120 \text{ K} \leq T \leq 300 \text{ K}$. As T decreases, S_w at $V_d = 0$ V (black circles) decreases exhibiting a linear relationship with the slope value of unity as also seen in **Fig. 5**, whereas S_w at $V_d > 0$ V remains higher than the thermal noise, clearly demonstrating that shot noise becomes predominant at low temperatures. We believe that detailed description of this behavior using the Fano factor [7], for example, will provide predictive noise modeling at cryogenic temperatures.

Conclusion

We have demonstrated variable-temperature characterization of N-MOSFETs, using the precisely calibrated PCB *vehicle* for broadband noise measurements from flicker noise to white noise. In order to build physics-based predictive models for developed MOSFETs, actual temperature-dependent measurements of broadband noise are necessary. Our measurement data show that a cryogenic environment reduces white noise at $V_d = 0$ V, but does not reduce $1/f$ and shot noise at $V_d \neq 0$ V, which will be a problematic noise source for quantum computing.

The lowest temperature for noise characterization was limited to 120 K in this study because bipolar transistors were adopted for the LNA. We believe that our methodology proposed here can be extended down to 4 K or below by designing an LNA composed of MOS transistors.

Acknowledgments

The authors gratefully acknowledge the cooperative research with Prof. R. Hasunuma of University of Tsukuba.

References

- [1] F. Sebastiano, et al., Proceedings of the 54th Annual Design Automation Conference 2017.
- [2] A. Beckers, F. Jazaeri, and C. Enz, IEEE. Electron Device Lett. 41, 276 (2020).
- [3] R. Landauer, Phys. Rev. B 47, 16427 (1993).
- [4] Y. Tsvividis and C. McAndrew, *Operation and Modeling of the MOS Transistor*, 3rd edition (Oxford University Press, 2011).
- [5] K. Ohmori, et al., 2013 Symposium on VLSI Circuits Digest of Technical Papers, C40.
- [6] <http://www.devicelab.co.jp>
- [7] K. Ohmori and S. Amakawa, submitted.
- [8] A. van der Ziel, *Noise in Solid State Devices and Circuits* (John Wiley & Sons, Inc., New York 1986).
- [9] L. Chua, Appl. Phys. A, 102, 765 (2011).
- [10] C. Beenakker and C. Schöenberger, Phys. Today 56, 37 (2003).

Fig. 1. Schematic of a cryogenic system with a PCB vehicle for wideband noise measurement.

Fig. 2. (a) Typical $I_d V_g$ property and (b) transconductance g_m for T ranging from 5 to 300 K.

Fig. 3. V_{th} and SS as a function of T .

Fig. 4. Noise spectral density obtained at $V_d = 0$ V and at $T =$ (a) 300 K and (b) 121 K. Under the same bias condition, white noise at $T = 121$ K is smaller than that at $T = 300$ K.

Fig. 5. Correlation between S_{id} and thermal noise ($4k_B T/R_{dif}$) at $V_d = 0$ V for V_g ranging from 0.8 to 1.6 V.

Fig. 6. Noise spectral density obtained at $V_g = 1.2$ V and at $T =$ (a) 300 K and (b) 130 K. As V_d increases, $1/f$ noise appears and white noise increases.

Fig. 7. Corner frequency f_c as a function of T .

Fig. 8. Dependences of S_{id} on V_d for $V_g = 1.2$ V at $T =$ (a) 300 K and (b) 130 K. The intensity of estimated white noise is between S_{th} and $2qI_d + S_{th}$. The V_d value at which $2qI_d = S_{th}$ is determined by $2k_B T/q$ at each T , where the increase of S_w is actually observed.

Fig. 9. Correlation between S_{id} and thermal noise S_{th} ($4k_B TR_{ch}/R_{dif}^2$) at $V_g = 1.2$ V for V_d ranging from 0 to 0.08 V.